



AmericanBiltrite

Grout repair procedure



1. Prior to any repair procedure, a full cleaning of the flooring should be performed.
2. Using a carbide scoring knife, carefully groove along the damaged grout line to prepare the surface for enhanced bonding between old and new grout.
3. Make sure to remove any loose grout material generated by this procedure.





AmericanBiltrite

4. Apply new pre-mixed grout over previously grooved grouting.
5. Allow sufficient time for the new grout to partially dry (normally 3 to 5 minutes)
6. Humidify a white light duty scouring pad (also known as Doodlebug), lightly scrub in an angular motion across the seams to loosen excess material from grooved areas and tile edges



7. With a rectangular sponge clean all excess materials from the tile surface and allow the surrounding areas to dry.



Franco Cicchino
Field Technical Services Director